

# PRODUCT DATA SHEET

Date: August 2009	Product Name: Brown - Everyday Life™ Pavers	
Product Code: 23893	 	
Description:		
Manufactured: Plant 23, Horsley Park, NSW		
Application:		

Typical Properties	
Length (mm)	230mm
Width (mm)	114mm
Height (mm)	55mm
Dimensional Category	DPA1
Average Weight / Unit	3.1kg
Units per Square Metre	37
Pack Size	530
Characteristic Breaking Load	>5kN
24 Hour Cold Water Absorption	<7 %
Mean Abrasion Resistance	<3.5cm <sup>3</sup>
Estimated 15 year Coefficient of Expansion (e factor)	<1.2mm/m
Slip Resistance Category	W
Durability Class	General Purpose

This data represents average results from commercial production lots. If specific test results are required, samples should be taken from current production lots.  
AUSTRALIAN STANDARD TEST METHODS AS/NZS 4456 ARE USED AS APPLICABLE.

Specifications											
Product Code	Product Name	Dimensions			Dimensional Category	Weight (kg)	Breaking Load (kN)	e' Factor (mm/m)	Durability	Abrasion Resistance (cm <sup>3</sup> )	Slip Resistance Category
		Length (mm)	Width (mm)	Height (mm)							
23892-1	Red	230	114	55	DPA1	3.1	>5	<1.2	General Purpose	<3.5	W
23893-1	Brown	230	114	55	DPA1	3.1	>5	<1.2	General Purpose	<3.5	W
23894-1	Grey	230	114	55	DPA1	3.1	>5	<1.2	General Purpose	<3.5	W
23895-1	Cream	230	114	55	DPA1	3.1	>5	<1.2	General Purpose	<3.5	W

# PRODUCT DATA SHEET

Date: August 2009	Product Name: Cream - Everyday Life™ Pavers	
Product Code: 23895		
Description:		
Manufactured: Plant 23, Horsley Park, NSW		
Application:		

Typical Properties	
Length (mm)	230mm
Width (mm)	114mm
Height (mm)	55mm
Dimensional Category	DPA1
Average Weight / Unit	3.1kg
Units per Square Metre	37
Pack Size	530
Characteristic Breaking Load	>5kN
24 Hour Cold Water Absorption	<7 %
Mean Abrasion Resistance	<3.5cm <sup>3</sup>
Estimated 15 year Coefficient of Expansion (e factor)	<1.2mm/m
Slip Resistance Category	W
Durability Class	General Purpose

This data represents average results from commercial production lots. If specific test results are required, samples should be taken from current production lots.  
AUSTRALIAN STANDARD TEST METHODS AS/NZS 4456 ARE USED AS APPLICABLE.

Specifications											
Product Code	Product Name	Dimensions			Dimensional Category	Weight (kg)	Breaking Load (kN)	e' Factor (mm/m)	Durability	Abrasion Resistance (cm <sup>3</sup> )	Slip Resistance Category
		Length (mm)	Width (mm)	Height (mm)							
23892-1	Red	230	114	55	DPA1	3.1	>5	<1.2	General Purpose	<3.5	W
23893-1	Brown	230	114	55	DPA1	3.1	>5	<1.2	General Purpose	<3.5	W
23894-1	Grey	230	114	55	DPA1	3.1	>5	<1.2	General Purpose	<3.5	W
23895-1	Cream	230	114	55	DPA1	3.1	>5	<1.2	General Purpose	<3.5	W

# PRODUCT DATA SHEET

Date: August 2009	Product Name: Grey - Everyday Life™ Pavers	
Product Code: 23894		
Description:		
Manufactured: Plant 23, Horsley Park, NSW		
Application:		

Typical Properties	
Length (mm)	230mm
Width (mm)	114mm
Height (mm)	55mm
Dimensional Category	DPA1
Average Weight / Unit	3.1kg
Units per Square Metre	37
Pack Size	530
Characteristic Breaking Load	>5kN
24 Hour Cold Water Absorption	<7 %
Mean Abrasion Resistance	<3.5cm <sup>3</sup>
Estimated 15 year Coefficient of Expansion (e factor)	<1.2mm/m
Slip Resistance Category	W
Durability Class	General Purpose

This data represents average results from commercial production lots. If specific test results are required, samples should be taken from current production lots.  
AUSTRALIAN STANDARD TEST METHODS AS/NZS 4456 ARE USED AS APPLICABLE.

Specifications											
Product Code	Product Name	Dimensions			Dimensional Category	Weight (kg)	Breaking Load (kN)	e' Factor (mm/m)	Durability	Abrasion Resistance (cm <sup>3</sup> )	Slip Resistance Category
		Length (mm)	Width (mm)	Height (mm)							
23892-1	Red	230	114	55	DPA1	3.1	>5	<1.2	General Purpose	<3.5	W
23893-1	Brown	230	114	55	DPA1	3.1	>5	<1.2	General Purpose	<3.5	W
23894-1	Grey	230	114	55	DPA1	3.1	>5	<1.2	General Purpose	<3.5	W
23895-1	Cream	230	114	55	DPA1	3.1	>5	<1.2	General Purpose	<3.5	W

# PRODUCT DATA SHEET

Date: August 2009	Product Name: Red - Everyday Life™ Pavers	
Product Code: 23892		
Description:		
Manufactured: Plant 23, Horsley Park, NSW		
Application:		

Typical Properties	
Length (mm)	230mm
Width (mm)	114mm
Height (mm)	55mm
Dimensional Category	DPA1
Average Weight / Unit	3.1kg
Units per Square Metre	37
Pack Size	530
Characteristic Breaking Load	>5kN
24 Hour Cold Water Absorption	<7 %
Mean Abrasion Resistance	<3.5cm <sup>3</sup>
Estimated 15 year Coefficient of Expansion (e factor)	<1.2mm/m
Slip Resistance Category	W
Durability Class	General Purpose

This data represents average results from commercial production lots. If specific test results are required, samples should be taken from current production lots.  
AUSTRALIAN STANDARD TEST METHODS AS/NZS 4456 ARE USED AS APPLICABLE.

Specifications											
Product Code	Product Name	Dimensions			Dimensional Category	Weight (kg)	Breaking Load (kN)	e' Factor (mm/m)	Durability	Abrasion Resistance (cm <sup>3</sup> )	Slip Resistance Category
		Length (mm)	Width (mm)	Height (mm)							
23892-1	Red	230	114	55	DPA1	3.1	>5	<1.2	General Purpose	<3.5	W
23893-1	Brown	230	114	55	DPA1	3.1	>5	<1.2	General Purpose	<3.5	W
23894-1	Grey	230	114	55	DPA1	3.1	>5	<1.2	General Purpose	<3.5	W
23895-1	Cream	230	114	55	DPA1	3.1	>5	<1.2	General Purpose	<3.5	W